



Description	Geometric pore size	Thickness	Porosity	Pressure Drop	As	Rp	Weight	specific flow-rate ratio	
	$\mu\text{m}$	mm	%	mbar	$\text{mm}^2 / \text{cm}$	N / cm	kg / $\text{m}^2$	Eu	
Absolta	Absolta 2	10	2.5	55	4.3	4.9	780	9	3254
	Absolta 5	14	2.5	55	3.3	4.9	780	9	2498
	Absolta 10	21	2.5	55	2.25	4.9	780	9	1703
	Absolta 15	20	2.5	55	1.46	4.9	780	8.5	1105
	Absolta 20	25	2.5	55	0.61	4.9	780	8.5	462
	Absolta 30	35	2.5	55	0.53	4.9	780	8.5	401
	Absolta 40	50	2.5	55	0.4	4.9	780	8.5	303
	Absolta 50	60	2.5	55	0.29	4.9	780	9	219
	Absolta 60	75	2.5	55	0.19	4.9	780	9	144
	Absolta 75	90	2.5	55	0.08	4.9	780	9	61

Version: 01.05.2015