



Sintergewebe	Bezeichnung	Geometrische Porengrösse	Dicke	Porösität	Druckverlust	As	Rp	Gewicht	spez. Durchfluss-Kennzahl
		µm	mm	%	mbar	mm ² / cm	N / cm	kg / m ²	Eu
Topmesh 3-lagig	TM3-KT 2	10	2	60	3.54	3.6	573	6.6	2682
	TM3-KT 5	14	2	60	2.77	3.6	573	6.6	2099
	TM3-KT 10	21	2	60	1.72	3.6	573	6.6	1298
	TM3-BM 15	15	2	60	0.62	3.6	573	6.6	469
	TM3-BM 20	20	2	60	0.58	3.6	573	6.2	439
	TM3-BM 25	25	2	60	0.47	3.6	573	6.2	356
	TM3-BM 30	30	2	60	0.35	3.6	573	6.2	265
	TM3-QM 40	42	2	60	0.13	3.6	573	6.1	98
	TM3-QM 50	50	2	60	0.11	3.6	573	6.1	83
	TM3-QM 60	63	2	60	0.08	3.6	573	6.1	61
	TM3-QM 80	80	2	60	0.07	3.6	573	6.1	53
	TM3-QM 100	100	2	60	0.07	3.6	573	6.2	53
	TM3-QM 150	160	2	60	0.06	3.6	573	6.2	45
	TM3-QM 200	200	2	60	0.06	3.6	573	6.2	45
	TM3-QM 500	530	2	60	0.03	3.6	573	6.2	23

Version: 01.05.2015